



## CMI PLASTER BONDING AGENT 370



### DESCRIPTION

CMI Plaster Bonding Agent 370 is a specifically formulated latex emulsion for bonding of cement-based plaster onto smooth concrete surface. It is blended with quartz sand to improve adhesion onto the substrate. CMI Plaster Bonding Agent 370 is characterized by its good alkali and water resistance.

### USES

To improve adhesion of render onto smooth concrete surface

### TECHNICAL DATA

Appearance	: Bluish milky liquid
Density	: Approx. 1.50 kg/liter
pH	: Approx. 8.0 - 9.0
Drying Time	: Approx. 2 hours
Application Temperature	: +5°C to 35°C

### SURFACE PREPARATION

All surfaces must be sound, clean and free from dirt, dust, grease and other contaminants which will inhibit proper bonding. Remove any brittle, soft and weakly bonded material from the surface of concrete.

### MIXING

Stir the product prior to usage as the sand might settled at the bottom of the pail.

### APPLICATION

Apply the product by painting and rolling onto the surface of concrete. Plaster can be applied while the product is still tacky or alternatively wait for it to fully dry before any subsequent works. It can be over-coated after the first coat had dried for at least 1 hour.

### COVERAGE

Approx. 200 – 250 g/m<sup>2</sup>

### PACKAGING

Available in 20 litres pail

### SHELF LIFE & STORAGE

Twelve (12) months when stored in cool and dry condition

#### CMI CONSTRUCTION MATERIAL INDUSTRY SDN BHD (422636-D)

No. 7, Jalan Sungai Jerluh 32/196, Bukit Kemuning  
Section 32, 40460 Shah Alam, Selangor.

Tel: 603-5131 9325 / 9425 Fax: 603-5131 8325 Email: enquiry@cmimalaysia.com.my

[www.cmimalaysia.com.my](http://www.cmimalaysia.com.my)



**Delivering  
Dry-Mix Solutions**

Remark: The information provided on this data sheet is not intended to be complete and is provided as general advice only. It is the user's responsibility to ensure that the product is suitable for its intended purpose. As we have no control over the treatment of the product, the standard of surface preparation, or other factors, we are not responsible for any damages or injury, including but not limited to special or consequential damages which may result from the use of our products, which includes any damages or injury caused by any failure of performance. The information contained in this data sheet may be modified by us from time to time, without any notice arising from our continuous product development activities.